



Designation: C1065 – 08 (Reapproved 2022)

Standard Specification for Nuclear-Grade Zirconium Oxide Powder¹

This standard is issued under the fixed designation C1065; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification defines the physical and chemical requirements for zirconium oxide powder intended for fabrication into shapes, either entirely or partially of zirconia, for use in a nuclear reactor core.

1.2 The material described herein shall be particulate in nature.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C117 Test Method for Materials Finer than 75- μ m (No. 200) Sieve in Mineral Aggregates by Washing

C371 Test Method for Wire-Cloth Sieve Analysis of Non-plastic Ceramic Powders

C859 Terminology Relating to Nuclear Materials

C1233 Practice for Determining Equivalent Boron Contents of Nuclear Materials

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E105 Guide for Probability Sampling of Materials

2.2 *ANSI Standard:*³

ANSI/ASME NQA-1 Quality Assurance Requirements for Nuclear Facility Applications

¹ This specification is under the jurisdiction of ASTM Committee C26 on Nuclear Fuel Cycle and is the direct responsibility of Subcommittee C26.03 on Neutron Absorber Materials Specifications.

Current edition approved July 1, 2022. Published July 2022. Originally approved in 1987. Last previous edition approved in 2015 as C1065 – 08 (2015). DOI: 10.1520/C1065-08R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

2.3 *U.S. Government Standard:*⁴

Code of Federal Regulations, Title 10, Part 50, Energy (10 CFR 50) Domestic Licensing of Production and Utilization Facilities

3. Terminology

3.1 Terms shall be defined in accordance with Terminology C859 except for the following:

3.2 *buyer*—the organization issuing the purchase order.

3.3 *phase transformation*—the rearrangement of the atomic ordering of a crystalline lattice as a material is cycled through a critical transformation or inversion temperature. The change from one crystalline phase to another may be accompanied by a volume change that could lead to cracks or defects in products fabricated from such materials.

3.4 *powder lot*—a specified quantity of zirconium oxide powder (with stabilizing additive, if applicable) blended together such that samples taken in accordance with the procedures of Section 8 can be considered as representative of the entire specified quantity.

3.5 *seller*—the zirconium oxide processor.

3.6 *stabilizing additive*—a material which, when added in sufficient quantity to the subject material exhibiting the phase transformation, produces a stabilized crystalline phase that does not undergo a transformation at any temperature within the expected fabrication or usage regime of the manufactured product; the potentially deleterious volume change is therefore avoided.

4. Ordering Information

4.1 The buyer shall specify the following information on the order:

4.1.1 Quantity (weight of delivered product).

4.1.2 Nominal particle size range and applicable tolerances in accordance with U.S. Standard Sieve Series (Specification E11). Test Method C371 and Test Method C117 and Specification E11 may be applied for particles larger than 37 μ m. For

⁴ Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, <http://www.access.gpo.gov>.