



Designation: D1073 – 16 (Reapproved 2022)

Standard Specification for Fine Aggregate for Asphalt Paving Mixtures¹

This standard is issued under the fixed designation D1073; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers fine aggregate for use in asphalt paving mixtures.

1.2 This specification is intended to describe material from a single source. When material from two or more sources is to be blended to produce a grading to meet requirements in other specifications for asphalt paving mixtures, the grading requirements of **Table 1** of this specification are not applicable.

NOTE 1—When obtaining materials from two or more sources that are to be blended to produce the final mix, it is recommended that the specifying or the ordering agency specify the alternative gradings and blend ratios to be supplied.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard. Sieve numbers shown in the text and **Table 1** are labels only and are included for ease of reference of the user of this standard.

1.4 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

C88/C88M Test Method for Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.50 on Aggregate Specifications.

Current edition approved July 1, 2022. Published July 2022. Originally approved in 1949. Last previous edition approved in 2016 as D1073 – 16. DOI: 10.1520/D1073-16R22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C117 Test Method for Materials Finer than 75- μ m (No. 200) Sieve in Mineral Aggregates by Washing
C125 Terminology Relating to Concrete and Concrete Aggregates
C136/C136M Test Method for Sieve Analysis of Fine and Coarse Aggregates
C294 Descriptive Nomenclature for Constituents of Concrete Aggregates
D8 Terminology Relating to Materials for Roads and Pavements
D75/D75M Practice for Sampling Aggregates
D3665 Practice for Random Sampling of Construction Materials
D4318 Test Methods for Liquid Limit, Plastic Limit, and Plasticity Index of Soils
E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

3. Terminology

3.1 Definitions:

3.1.1 For defining aggregate types, see Descriptive Nomenclature **C294**, and Terminologies **D8** and **C125**.

3.1.2 *expanded shale, n; expanded clay, n; expanded slate, n*; the product resulting from the expanding of selected materials (shale, clay, or slate) in a rotary kiln at temperatures over 1000 °C.

4. Ordering Information

4.1 Orders for material under this specification shall include the following:

4.1.1 This specification designation including year,

4.1.2 Grading (**6.2** and **Table 1**), or alternative grading designated by the purchaser,

4.1.3 Supplementary requirement for sulfate soundness, if required, including salt to be used (See Supplementary Requirement S1), and

4.1.4 Any exceptions or additions to this specification.

5. General Characteristics

5.1 Fine aggregate is aggregate passing the 9.5 mm ($\frac{3}{8}$ in.) sieve and almost entirely passing the 4.75 mm (No. 4) sieve. It shall consist of natural sand; or of manufactured fine aggregate