



Standard Specification for Solvent Cement for Acrylonitrile-Butadiene-Styrene (ABS) Plastic Pipe and Fittings¹

This standard is issued under the fixed designation D2235; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ε) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers solvent cement for joining acrylonitrile-butadiene styrene (ABS) plastic pipe and fittings for pressure and nonpressure systems.

1.2 Recommendation for using solvent cement for joining acrylonitrile-butadiene-styrene (ABS) plastic pipe and fittings is given in [Appendix X1](#). Satisfactory joining of pipe and fittings cannot be made in the presence of water, as water destroys the bonding ability of solvent cement; therefore, all materials must be dry for satisfactory joining.

1.3 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 The following safety hazards caveat pertains only to the test methods portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- [D329 Specification for Acetone](#)
- [D618 Practice for Conditioning Plastics for Testing](#)
- [D740 Specification for Methyl Ethyl Ketone](#)
- [D883 Terminology Relating to Plastics](#)
- [D1084 Test Methods for Viscosity of Adhesives](#)
- [D1527 Specification for Acrylonitrile-Butadiene-Styrene \(ABS\) Plastic Pipe, Schedules 40 and 80 \(Withdrawn 2013\)³](#)
- [D2282 Specification for Acrylonitrile-Butadiene-Styrene \(ABS\) Plastic Pipe \(Withdrawn 2006\)³](#)
- [D2465 Specification for Threaded Acrylonitrile-Butadiene-Styrene \(ABS\) Plastic Pipe Fittings, Schedule 80 \(Withdrawn 1985\)³](#)
- [D2468 Specification for Acrylonitrile-Butadiene-Styrene \(ABS\) Plastic Pipe Fittings, Schedule 40 \(Withdrawn 2003\)³](#)
- [D2469 Specification for Socket-Type Acrylonitrile-Butadiene-Styrene \(ABS\) Plastic Pipe Fittings, Schedule 80 \(Withdrawn 1985\)³](#)
- [D2661 Specification for Acrylonitrile-Butadiene-Styrene \(ABS\) Schedule 40 Plastic Drain, Waste, and Vent Pipe and Fittings](#)
- [D2680 Specification for Acrylonitrile-Butadiene-Styrene \(ABS\) and Poly\(Vinyl Chloride\) \(PVC\) Composite Sewer Piping](#)
- [D2750 Specification for Acrylonitrile-Butadiene-Styrene \(ABS\) Plastics Utilities Conduit and Fittings \(Withdrawn 1997\)³](#)
- [D2751 Specification for Acrylonitrile-Butadiene-Styrene \(ABS\) Sewer Pipe and Fittings \(Withdrawn 2014\)³](#)
- [D1600 Terminology for Abbreviated Terms Relating to Plastics](#)

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.20 on Joining.

Current edition approved July 1, 2022. Published July 2022. Originally approved in 1963. Last previous edition approved 2021 as D2235 – 21. DOI: 10.1520/D2235-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

D3965 Classification System and Basis for Specifications for Rigid Acrylonitrile-Butadiene-Styrene (ABS) Materials for Pipe and Fittings

F402 Practice for Safe Handling of Solvent Cements, Primers, and Cleaners Used for Joining Thermoplastic Pipe and Fittings

F409 Specification for Thermoplastic Accessible and Replaceable Plastic Tube and Tubular Fittings

F412 Terminology Relating to Plastic Piping Systems

F493 Specification for Solvent Cements for Chlorinated Poly(Vinyl Chloride) (CPVC) Plastic Pipe and Fittings

F628 Specification for Acrylonitrile-Butadiene-Styrene (ABS) Schedule 40 Plastic Drain, Waste, and Vent Pipe With a Cellular Core

2.2 *Federal Standard:*

Fed. Std. 123 Marking for Shipment (Civil Agencies)⁴

2.3 *Military Standard:*

MIL STD-129 Marking for Shipment and Storage⁴

2.4 *National Sanitation Foundation Standards:*

Standard No. 14 Plastic Piping Components and Related Materials⁵

Standard No. 61 for Drinking Water Systems Components—Health Effects⁵

3. Terminology

3.1 Definitions are in accordance with Terminologies **D883** and **F412**. Abbreviations are in accordance with Terminology **D1600** unless otherwise indicated. The abbreviation for Acrylonitrile-Butadiene-Styrene plastic is ABS.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *solvent cement*—adhesive made by dissolving a plastic resin or compound in a suitable solvent or mixture of solvents. The solvent cement dissolves the surfaces of the pipe and fittings to form a bond between the mating surfaces provided the proper cement is used for the particular materials and proper techniques are followed.

4. Classification

4.1 Solvent Cement shall be acrylonitrile-butadiene-styrene plastic resin dissolved in either of the following solvents:

(1) methyl ethyl ketone,

(2) a blend of methyl ethyl ketone and acetone, with acetone constituting no more than 25 % of the solvent blend by weight,

(3) a blend of methyl ethyl ketone and cyclohexanone, with cyclohexanone constituting no more than 25 % of the solvent weight by blend,

(4) a blend of methyl ethyl ketone, acetone and cyclohexanone, with cyclohexanone and acetone respectively constituting no more than 25 % of the solvent weight by blend.

NOTE 1—It is recommended that solvent cements made to this specification *not* be orange since that color is recommended for use with CPVC solvent cement under Specification **F493**.

5. Materials

5.1 *Material Specification*—Virgin ABS material shall conform to the requirements prescribed in Specification **D3965** with a minimum cell classification of 1-1-2-2-2 or equivalent to the cell classification for the material being joined.

5.2 *Acrylonitrile-Butadiene-Styrene (ABS) Plastic*—Plastic containing polymers in which the minimum butadiene content is 6 %, the minimum acrylonitrile content is 15 %, the minimum styrene or substituted styrene content, or both, is 15 %, and the maximum content of all other monomers is not more than 5 %.

5.3 *Rework Material*—Only clean regrind material conforming to the requirements of this specification may be used.

5.4 *Methyl Ethyl-Ketone*—Commercial or industrial grade of MEK shall be used which complies with Specification **D740**.

5.5 *Acetone*—Commercial or industrial grade of acetone shall be used which complies with Specification **D329**.

6. Requirements

6.1 *Resin Content*—The ABS resin content shall be 15 % minimum when tested in accordance with **7.3**.

6.2 *Dissolution*—The cement shall be capable of dissolving 10 % by weight of the plastic compound used in the pipe or fitting, and still be free flowing and not contain lumps or undissolved resin particles.

6.3 The cement shall be free flowing and shall not contain lumps, undissolved particles, or foreign matter. It shall show no gelation or separation that cannot be removed by stirring.

6.4 *Viscosity*—The minimum viscosity shall be 100 cP (100 mPa·s) when tested in accordance with **7.2.2**.

6.5 *Lap Shear Strength*—The minimum average lap shear strength shall be 800 psi (5.5 MPa) when tested in accordance with **7.4**.

NOTE 2—The specified shear strength value is used to evaluate the cement and should not be used for designing pipe joints.

7. Test Methods

7.1 The properties enumerated in this specification shall be determined in accordance with the following methods:

7.1.1 *Conditioning*—Condition the test specimens at 73.4 °F ± 3.6 °F (23 °C ± 2 °C) for not less than 40 h prior to test in accordance with Procedure A of Practice **D618**, for those tests where conditioning is required.

7.1.2 *Test Conditions*—Conduct tests at 73.4 °F ± 3.6 °F (23 °C ± 2 °C), unless otherwise specified in the test methods or in this specification.

7.2 *Viscosity:*

7.2.1 The samples for test shall be representative of the material under consideration. One sample for every batch shall be tested in accordance with **7.2.2**.

7.2.2 Measure the viscosity in accordance with Method B of Test Methods **D1084**, except that conditioning to temperature equilibrium only is required. For qualification purposes, use a Model RVF viscometer, a speed of 10 r/min, and the spindle

⁴ Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil>.

⁵ Available from NSF International, P.O. Box 130140, 789 N. Dixboro Rd., Ann Arbor, MI 48113-0140, <http://www.nsf.org>.