



Designation: D6575/D6575M – 22

Standard Test Method for Determining Stiffness of Geosynthetics Used as Turf Reinforcement Mats (TRMs)¹

This standard is issued under the fixed designation D6575/D6575M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope

1.1 This test method covers the determination of the stiffness of geosynthetics used as turf reinforcement mats (TRMs).

1.2 The method is applicable to TRMs of any fiber content and any number of components.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

[D123 Terminology Relating to Textiles](#)

[D1388 Test Method for Stiffness of Fabrics](#)

[D1776/D1776M Practice for Conditioning and Testing Textiles](#)

[D4354 Practice for Sampling of Geosynthetics and Rolled Erosion Control Products \(RECPs\) for Testing](#)

[D4439 Terminology for Geosynthetics](#)

¹ This test method is under the jurisdiction of ASTM Committee [D35](#) on Geosynthetics and is the direct responsibility of Subcommittee [D35.05](#) on Geosynthetic Erosion Control.

Current edition approved July 1, 2022. Published July 2022. Originally approved in 2000. Last previous edition approved in 2016 as D6575/D6575M – 16. DOI: 10.1520/D6575_D6575M-22.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D6566 Test Method for Measuring Mass Per Unit Area of Turf Reinforcement Mats](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

2.2 Federal Standards:³

[CCC-T-191b Textile Test Methods No. 5206.2](#)

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *bending length (general), n*—a measure of the interaction between geosynthetic weight and geosynthetic stiffness as shown by the way in which a geosynthetic bends under its own weight. It reflects the stiffness of a geosynthetic when bent in one plane under the force of gravity, and is one component of drape.

3.1.1.1 *Discussion*—Bending length is called “drape stiffness” in Federal Specification CCC-T-191b.

3.1.2 *bending length (specific), n*—the cube root of the ratio of the flexural rigidity to the mass per unit area.

3.1.3 *flexural rigidity (general), n*—resistance to bending.

3.1.3.1 *Discussion*—Resistance to bending or flexural rigidity is called “flex stiffness” in Federal Specification CCC-T-191b.

3.1.4 *flexural rigidity (specific), n*—the couple on either end of a sample of unit width bent into unit curvature in the absence of any tension.

3.1.4.1 *Discussion*—The methods measure the bending length. Flexural rigidity is calculated directly by multiplying the cube of the bending length by the weight per unit area (see [3.1.2](#)).

3.1.5 *stiffness, n*—resistance to bending.

3.2 *Definitions*—For definitions of other textile or geosynthetic terms used in this test method, refer to Terminologies [D123](#) and [D4439](#).

³ Available from U.S. Government Publishing Office, 732 N. Capitol St., NW, Washington, DC 20401-0001, <http://www.gpo.gov>.



4. Significance and Use

4.1 In general this test method is adapted from tests developed for woven fabrics (previously designated as Test Method [D1388](#)).

4.2 The cantilever test method may not be suitable for testing products that are very limp or have a marked tendency to curl or twist at a cut edge.

Cantilever Method

5. Summary of Method

5.1 A specimen of the TRM is slid in a direction parallel to its long dimension, so that its end projects from the edge of a horizontal surface. The length of overhang is measured when the tip of the test specimen is depressed under its own weight to the point where the line joining the tip to the edge of the platform makes an angle of 41.5° with the horizontal. One half of this length is the bending length of the specimen. The cube of this quantity multiplied by the weight per unit area of the geosynthetic is the flexural rigidity.

5.2 This test method is known also as the Single Cantilever Test.

6. Apparatus

6.1 *Stiffness Tester*, having the following parts:

6.1.1 *Horizontal Platform*, with a minimum area of 18 by 12 in. [457.2 by 304.8 mm] and having a smooth low-friction, flat surface such as polished metal or plastic. A leveling bubble shall be incorporated in the platform, or be available for verification that the horizontal platform is level.

6.1.2 *Indicator*, inclined at an angle of 41.5° below the plane of the platform surface.

6.1.3 *Weight*, consisting of a metal bar not less than 4 by 18 in. [101.6 by 457.2 mm] by about $\frac{1}{8}$ in. [3 mm] thick.

6.1.4 *Scale and Pointer*, to measure the length of the overhang.

7. Conditioning

7.1 For tests made as directed in [9.1 – 9.5](#), bring the sample to a moisture equilibrium in the atmosphere for testing TRMs, that is, a temperature of $70 \pm 4^\circ\text{F}$ [$21 \pm 2^\circ\text{C}$] and relative humidity of $60 \pm 10\%$. See Practice [D1776/D1776M](#).

7.2 Additional conditioning may be needed to remove curl from rolled geosynthetics. See Practice [D4354](#).

8. Selection and Preparation of Specimens

8.1 Cut test specimens 4 in. wide by a minimum of 18 in. long [101.6 by 457.2 mm]; longer specimens may be needed to obtain a measurement. At least 6 in. [152.4 mm] of the specimen should remain under the sliding plate at the point of measurement. Cut four specimens with the long direction parallel to the machine direction and four with the long direction parallel to the transverse (or cross-machine) direction. If the geosynthetic is not uniform or a higher degree of precision is required, more may be tested. Vary cutting the specimens in such a way that the machine direction specimens do not contain the same machine direction yarns/filaments for

the machine direction tests and cut the cross-machine direction specimens so that separate cross-machine direction yarns/filaments are contained in each. Avoid selvages, end pieces, and creased or folded places, and handle the specimens as little as possible.

NOTE 1—Some TRMs are constructed from several component materials and sample preparation must be performed in such a way as to maintain the structural integrity of the product. Procedures found to be successful for cutting test specimens from TRMs include the use of hot knives to seal the edges and the use of bags and slip covers to keep all components together during sample preparation. The method of cutting the specimen should be included in the report.

9. Procedure

9.1 Make tests on conditioned specimens in the standard atmosphere for testing.

9.2 Set the tester on a table or bench so that the horizontal platform and inclined reference lines are at eye level. Adjust the platform so that it is horizontal as indicated by the leveling bubble.

9.3 Place a specimen on the platform with the weight on top of it so that the leading edges coincide. Holding the weight in a horizontal plane, slide the specimen and weight slowly and steadily until the leading edges project beyond the edge of the platform. Take the measurement of the overhang where the center of the leading edge of the specimen touches the incline. At least 6 in. [152.4 mm] of the specimen should remain under the sliding plate at the point the leading edge touches the measurement incline. Do not measure specimens that twist more than 45° . Read the length of overhang from the scale to the nearest 1 mm.

9.4 Take four readings from each specimen, with each side up, first at one end and then the other.

9.5 Determine the mass per unit area according to Test Method [D6566](#).

10. Calculation

10.1 Unless otherwise specified, average the four readings obtained from all the specimens cut parallel to the machine direction. Do the same for those cut parallel to the cross-machine direction. In some cases it may be of interest to differentiate between the sides of the geosynthetic by averaging those readings made with the face side up separately from those with the reverse side up. If this is done, specify the direction of bending. Call these averages the “length of overhang,” and express them in centimetres. Calculate the bending length, c , in centimetres, and the flexural rigidity, G , in mg/cm by [Eq 1 and 2](#):

$$\text{Bending length, } c = L_o/2 \quad (1)$$

where:

L_o = length of overhang, cm.

$$\text{Flexural rigidity, } G = W \times (L_o/2)^3 = W \times c^3 \quad (2)$$

where:

W = weight per unit area, mg/cm².

NOTE 2—To obtain the weight in mg/cm², multiply oz/yd² by 3.39. Federal Specification CCC-T-191b gives flexural rigidity in in.-lb. To